



T 30 G

T 30 G is a polypropylene homopolymer for injection moulding applications.

T 30 G combines high stiffness and fairly good impact strength with good processability. The grade is suitable for a wide range of applications such as housewares, caps, closures, small containers, toys, parts for small appliances and components for the automotive industry.



PROPERTIES	METHOD (b)	UNIT	TYPICAL VALUE (a)
Physical properties			
Melt flow rate (230°C, 2.16 kg)	ISO 1133	Dg / min	3.2
Density	ISO 1183	g/cm ³	0.9
Mechanical properties			
Flexural modulus	ISO 178	N/mm ²	1450
Tensile strength yield	ISO R 527	N/mm ²	34
Elongation at yield	ISO R 527	%	13
IZOD impact strength (notched) at 23°C	ISO 180	kJ/m ²	5
Hardness Shore D	ISO 868	Points	71
Thermal properties			
Vicat softening point (9.8 N)	ISO 306/A	°C	155
H.D.T. (0.46 Mpa)	ISO 75/B	°C	110
Accelerated oven ageing in air (forced circulation) at 150°C	ISO 4577	hours	360

● T 30 G is suitable for food contact.

a) Values shown are averages and are not to be considered as product specification. These values may shift slightly as additional data are accumulated.

b) ISO test methods are the latest under the society's current procedures.

All specimens are prepared by injection moulding.