



X 30 G

X 30 G is a polypropylene homopolymer for injection moulding. Because of its good flow properties, this grade offers easy processing.

Articles produced from X 30 G exhibit high stiffness. X 30 G is widely used for injection moulding consumer goods such as food containers, housewares, toys and garden furniture. Other major applications are components for appliances and parts for the automotive industry.



PROPERTIES	METHOD (b)	UNIT	TYPICAL VALUE (a)
Physical properties			
Melt flow rate (230°C, 2.16 kg)	ISO 1133	Dg / min	9
Density	ISO 1183	g/cm ³	0.9
Mechanical properties			
Flexural modulus	ISO 178	N/mm ²	1500
Tensile strength at yield	ISO R 527	N/mm ²	34
Elongation at yield	ISO R 527	%	13
IZOD impact strength (notched) at 23°C	ISO 180	kJ/m ²	4
Hardness Shore D	ISO 868	Points	71
Thermal properties			
Vicat softening point (9.8 N)	ISO 306/A	°C	155
H.D.T. (0.46 Mpa)	ISO 75/B	°C	115
Accelerated oven ageing in air (forced circulation) at 150°C	ISO 4577	hours	360

● X 30 G is suitable for food contact.

a) Values shown are averages and are not to be considered as product specification. These values may shift slightly as additional data are accumulated.

b) ISO test methods are the latest under the society's current procedures.

All specimens are prepared by injection moulding.